

TECHNICAL DATA SHEET

H2Foam Lite V8E™

PRODUCT CHARACTERISTICS

Construction Products: In-situ formed sprayed rigid polyurethane (PUR) foam products as covered by the scope of standard EN 14315-1.

H2Foam Lite V8E is a spray-in-situ low density, open celled, flexible, 100% water-blown polyurethane foam insulation manufactured by Icynene Inc. The product is for use as a thermal insulation and air barrier in: roofs, wall cavities, floor assemblies, ceiling assemblies, attics (vented and unvented), crawl spaces (vented and unvented). Can be sprayed onto: concrete and masonry, wood, gypsum board and particle board.

For more information, look Icynene H2Foam Lite V8E installation instructions.

FOAM PROPERTIES

Characteristic	Norme	Value
Thermal conductivity	EN 12 667	$\lambda_D = 0,037 \text{ W/(mK)}$
Density	EN 1602	6 - 8 kg/m ³
Reaction to fire	EN 13501-1	E
Vapor transmission	EN 12086	MU2,2
Water absorption	EN 1609	W0,3
Release of dangerous substances (VOC)	ISO 16000	A+
Dimensional stability	EN 1604	DS(TH)4

All tests are carried out in accordance with the standards specified in EN 14315-1-2013.

PHYSICAL AND CHEMICAL PROPERTIES

Component:	A	B
Physical state:	Liquid	Liquid
Color:	Brown	White
Odor:	Slight musty	Amine
Relative density:	1.23	1.1
Flash point:	>150°C	>93°C
Dynamic viscosity:	≥200 mPa·s at 20°C	700 cP at 25°C

RESIN CHARACTERISTICS

Characteristic	Result	Test method
pH:	11	AS-method
Specific Gravity:	1.1 g/mL	Pycnometer

STORAGE AND USAGE

H2Foam Lite V8E Component A and Component B ideally should be stored between 15°C and 30°C. Component A should be protected from freezing. Shelf life is 12 months. Use mixer at low speed. Do not store material on rigs other than what is required for current application needs. Material left inside of rigs can easily exceed these recommended temperatures, especially in warmer months. This excessive heat will degrade the Component B (Resin) material and shorten its usable shelf life. Do not store components in open drums. If material transporting was in freezing conditions, store it in room temperature for minimum 24 hours to get material proper condition. Do not use any additional heaters to heat up material during storage.

HEALTH AND SAFETY

- ✓ First AID KIT and Water station should be available in the truck
- ✓ In case of spills refer to MSDS
- ✓ For Homeowners

Icynene spray foam insulation products have an excellent health and safety record spanning. Nonetheless, safe handling practices during and immediately following installation are required to eliminate the possibility of health effects from exposure to isocyanates. Everyone (other than Icynene-certified spray technicians) must vacate the job site, remaining completely out of the building or at least 15 meters away, while the spray is applied and for at least 2 hours* after spraying is completed. It is necessary to allow active ventilation of the job site and to ensure the foam chemicals are completely cured. No exceptions.

- ✓ For Certified Sprayer

Direct contact with the skin and eyes can result in irritation. Different individuals will react differently to the same exposures; some will be more sensitive than others. Sprayers helpers, and anyone else present during spraying or within 1 hour** after spraying is complete: You must ventilate at 40ACH and must wear proper Personal Protective Equipment (PPE) at all times during spray, including full-body-coverage, chemical-protective clothing and a NIOSH-

Icynene Europe SPRL, Clos Chappelle aux Champs 30, Boite 3030, B-1200, Brussels, tel +32 2 880 62 33

www.icynene.eu

V. 12.12.2018

Page 3 of 5

certified respirator with fresh air supply. While spraying and for 1 hour** after spraying is completed, no one must be allowed within 15 meters of the sprayed foam without wearing this type of PPE at all times.

For full information, please refer to chapter 4 of Icynene installation instruction manual.

- ✓ Ventilation

RE-ENTRY AND RE-OCCUPANCY PERIODS

Times based upon ventilating during and after a spray application.

Ventilation Rate (Air Changes per Hour)	Re-entry period for sprayers, helpers, informed trade workers and contractors	Re-occupancy period for all others
At 0.3 ACH	24 hours	24 hours
At 1.0 ACH	12 hours*	24 hours
At 10.0 ACH	4 hours*	24 hours
At 40.0 ACH	1 hour**	2 hours**

*Twelve (12) and four (4) hour re-entry for trades applies to all Icynene products.

** One (1) hour re-entry and two (2) hour re-occupancy applies only to Low VOC products.

EXCEPTION: For installations of low VOC products.

reentry is permitted after 1 hour**

re-occupancy of the job site is permitted after 2 hours**

provided that ventilation rates are followed as recommended on this page.

Number of air changes per hour (ACH) can be calculated using the following formula:

$$ACH = \frac{Fan\ Power\ in\ l/s * 3,6}{Room\ Volume\ in\ m^3\ 2a}$$

If the number of ACH is not sufficient, a bigger fan or perhaps multiple fans may be used.

Icynene Europe SPRL, Clos Chappelle aux Champs 30, Boite 3030, B-1200, Brussels, tel +32 2 880 62 33

www.icynene.eu

V. 12.12.2018

Page 4 of 5

PACKAGE

The components are supplied in barrels with capacity of 200 l.

Component A – 249 kg

Component B – 226 kg

OTHER INFORMATION

All physicochemical properties were determined by testing in accredited laboratories. Icynene Europe reserve the right to change specifications to continuously improve the product.